Orton Pyrometric Cone Chart for cones 022-14

13*

14*

	Self Supporting Cones						Large Cones				Small
	Regular			Iron Free			Regular		Iron Free		Regular
	Heating Rate °F/hour (last 180°F of firing)										
Cone	27	108	270	27	108	270	108	270	108	270	540
022		1087	1094				N/A	N/A			1166
021		1112	1143				N/A	N/A			1189
020		1159	1180				N/A	N/A			1231
019	1213	1252	1283				1249	1279			1333
018	1267	1319	1353				1314	1350			1386
017	1301	1360	1405				1357	1402			1443
016	1368	1422	1465				1416	1461			1517
015	1382	1456	1504				1450	1501			1549
014	1395	1485	1540				1485	1537			1598
013	1485	1539	1582				1539	1578			1616
012	1549	1582	1620				1576	1616			1652
011	1575	1607	1641				1603	1638			1679
010	1636	1657	1679	1600	1627	1639	1648	1675	1623	1636	1686
09	1665	1688	1706	1650	1686	1702	1683	1702	1683	1699	1751
08	1692	1728	1753	1695	1735	1755	1728	1749	1733	1751	1801
07	1764	1789	1809	1747	1780	1800	1783	1805	1778	1796	1846
06	1798	1828	1855	1776	1816	1828	1823	1852	1816	1825	1873
051/2	1839	1859	1877	1814	1854	1870	1854	1873	1852	1868	1909
05	1870	1888	1911	1855	1899	1915	1886	1915	1890	1911	1944
04	1915	1945	1971	1909	1942	1956	1940	1958	1940	1953	2008
03	1960	1987	2019	1951	1990	1999	1987	2014	1989	1996	2068
02	1972	2016	2052	1983	2021	2039	2014	2048	2016	2035	2098
01	1999	2046	2080	2014	2053	2073	2043	2079	2052	2070	2152
1	2028	2079	2109	2046	2082	2098	2077	2109	2079	2095	2163
2	2034	2088	2127				2088	2124			2174
3	2039	2106	2138	2066	2109	2124	2106	2134	2104	2120	2185
4	2086	2124	2161				2120	2158			2208
5	2118	2167	2205				2163	2201			2230
51/2	2133	2197	2237				N/A	N/A			N/A
6	2165	2232	2269				2228	2266			2291
7	2194	2262	2295				2259	2291			2307
8	2212	2280	2320				2277	2316			2372
9	2235	2300	2336				2295	2332			2403
10	2284	2345	2381				2340	2377			2426
				1					ı		

2410*

2530*

2455*

2491*

N/A

N/A